



MAFLEX-CZ, s.r.o. Mosty u Jablunkova 145, 73998

VICKERS HV	ROCKWELL HRC	TENSILE STRENGTH N/mm2	BRINELL HB	EQUOTIP LD	SHORE C HSc
940	68.0	-	-	890	106
920	67.5	-	-	884	105
900	67.0	-	-	878	103
880	66.0	-	-	872	101
860	65.5	-	-	866	100
840	64.5	-	-	860	98
820	64.0	-	-	853	97
800	63.5	-	-	846	95
780	62.5	-	-	839	93
760	62.0	-	-	832	92
740	61.0	-	-	825	90
720	60.5	-	-	817	89
700	59.5	-	-	809	87
680	58.5	-	-	801	86
660	57.5	-	-	792	84
640	56.5	-	-	784	82
620	55.5	-	-	774	81
600	54.5	-	-	765	79
580	53.5	-	-	756	78
560	52.5	-	-	745	76
545	52.0	-	-	732	73
528	51.0	-	-	723	71.5
512	50.0	-	-	714	70
498	49.0	-	-	702	68
485	48.0	1525	450	693	66.5
473	47.0	1525	450	684	65
459	46.0	1408	436	675	63.5
446	45.0	1044	424	666	62
435	44.0	1400	413	657	60.5
423	43.0	1360	402	654	60
402	41.0	1295	382	648	59
392	40.0	1260	372	642	58
382	39.0	1225	363	636	57
373	38.0	1200	354	630	56
364	37.0	1165	346	624	55
355	36.0	1140	337	618	54
346	35.0	1110	329	612	53
337	34.0	1080	320	606	52
328	33.0	1050	312	594	50
310	31.0	995	295	582	48
302	30.0	970	287	576	47
294	29.0	945	279	570	46
287	28.0	920	273	560	45
279	27.0	900	265	550	43.5
273	26.0	875	259	547	43
266	25.0	855	253	533	42
260	24.0	835	247	527	41
254	23.0	820	241	521	40
250	22.0	800	238	516	39.5
244	21.0	780	232	510	39
239	20.0	765	227	505	38
233	-	750	221	499	37
226	-	725	214	491	36
218	-	700	207	483	35